



151 West Passaic Street, Rochelle Park, NJ 07662
Tel: 201-909-3767 Fax: 201-909-3769

"Your #1 Source for Chemical Foaming Agents"

Foamazol™ 61 **Chemical Foaming Agent**

PRODUCT DATA

Application

Intended for applications where maximum density reduction is required at relatively low processing temperatures. It is suitable for low pressure structural foam, injection molding, and extrusion.

Characteristics:

Endothermic Decomposition

Regulatory Status:

All Raw Materials Are GRAS (generally regarded as safe)

Physical Appearance:

Supplied as white pellets

Technical Data

Decomposition Range:

Beginning @ 145°C (293°F)

Processing Recommendations:

Maximum gas yields are achieved when processing temperatures of 175-215°C (347-419°F) are reached

Usage Levels

Injection Molding:

For cell size control, 0.25-0.75%
As a chemical foaming agent 0.5-1.5%

Extrusion:

0.25-1.5% for chemical foaming

The information and recommendations made herein are based on the research of others and are believed to be accurate. However, nothing herein is to be taken as a warranty, expressed or implied, regarding the accuracy of the information or the use of this product, and purchasers should make their own tests and evaluation to determine the suitability of this product in their application. Nothing herein is to be construed as a recommendation to use or as a license to operate under or to infringe any existing patents.



151 West Passaic Street, Rochelle Park, NJ 07662
Tel: 201-909-3767 Fax: 201-909-3769

"Your #1 Source for Chemical Foaming Agents"
