



411 Route 17 South, Suite 100  
Hasbrouck Heights, New Jersey 07604  
Tel: 201-299-4499 Fax: 201-335-5909

*"Your #1 Source for Chemical Foaming Agents"*

## Foamazol™ 57 Chemical Foaming Agent

## PRODUCT DATA

### Application

Recommended for foaming in injection molding and extrusion

Characteristics:

Endothermic Decomposition

Regulatory Status:

All Raw Materials Are GRAS (generally regarded as safe)

Physical Appearance:

Supplied as white pellets

### Technical Data

Decomposition Range:

Beginning @ 160°C (320°F)

Processing Recommendations:

Maximum gas yields are achieved when processing temperatures of 200-230°C (392-446°F) are reached

### Usage Levels

Injection Molding:

0.5-2.5% for chemical foaming

Extrusion:

0.2-1.5% for chemical foaming

The information and recommendations made herein are based on the research of others and are believed to be accurate. However, nothing herein is to be taken as a warranty, expressed or implied, regarding the accuracy of the information or the use of this product, and purchasers should make their own tests and evaluation to determine the suitability of this product in their application. Nothing herein is to be construed as a recommendation to use or as a license to operate under or to infringe any existing patents.